



IN THE CLAIMS

RECEIVED
DEC 03 2003
TC 1700

Please amend the claims as follows.

1. (Currently Amended) A carbonaceous active material comprising:
at least one crystalline graphite core; and
an amorphous graphitizable carbon shell coating the outside of the crystalline graphite core
wherein a differential thermal analysis conducted on the carbonaceous active material in 10°C
increments per minute starting from room temperature and proceeding to 1000°C at atmospheric
pressure results in the displaying of at least two exothermic peaks overlapping to form shoulders,
and

~~wherein the carbonaceous active material is prepared by a process comprising:~~
~~dissolving amorphous carbon in an organic solvent to produce a solution;~~
~~mixing crystalline graphite particles with the solution;~~
~~refluxing the mixture;~~
~~filtering the mixture to obtain a powder; and~~
~~heat treating the powder at approximately 1000°C to obtain the active material.~~
the amorphous graphitizable carbon shell coating is derived from an amorphous carbon
precursor selected from the group consisting of pitch, coal based oil and heavy oil.

2. (Original) The carbonaceous material of claim 1 wherein the at least two exothermic
peaks occur at a temperature of 500-1000°.

3. (Original) The carbonaceous material of claim 1 wherein the at least two exothermic
peaks occur at a temperature of 500-900°C.

4. (Original) The carbonaceous material of claim 1 wherein a difference in temperature
between the at least two exothermic peaks is less than 200°C.

5. (Original) The carbonaceous material of claim 1 wherein a peak intensity ratio of
the active material is 1 or less.

6. (Original) The carbonaceous material of claim 1 wherein the active material
includes at least one crystalline graphite primary particle coated with amorphous carbon, and the at

least one crystalline graphite primary particle coated with the amorphous carbon is agglomerated and made into a spherical shape to produce secondary particles.

7. (Cancelled)